

10-26-00

PTO/SD/05
Patent and Trademark Office U.S. DEPARTMENT OF COMMERCE
10/25/00

10/25/00

Please type a plus sign (+) inside this box → ☒

Under the Paperwork Reduction Act of 1995, no person is required to respond to a collection of information unless it displays a valid OMB control number.

UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 C.F.R. § 1.55(b))

Attorney Docket No. **T99,005-B**

First Inventor or Application Identifier **Eric Geiger**

Title **See 1 in Addendum**

Express Mail Label No. **EK323647096US**

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents

ADDRESS TO:

Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

- ☒ Fee Transmittal Form (p.g., PTO/SB/17)
(Submit an original and a duplicate for fee processing)
- ☒ Specification [Total Pages **52**]
(preferred arrangement set forth below)
- Descriptive title of the invention
- Cross References to Related Applications
- Statement Regarding Fed sponsored R & D
- Reference to Micro* che Appendix
- Background of the invention
- Brief Summary of the invention
- Brief Description of the Drawings (if filed)
- Detailed Description
- Claim(s)
- Abstract of the Disclosure
- ☐ Drawing(s) (35 U.S.C. 113) [Total Sheets ☐
- ☐ Oath or Declaration [Total Pages **3**]
a. ☒ Newly executed (original or copy)
b. ☐ Copy from a prior application (37 C.F.R. § 1.63(d))
(for continuation/divisional with Box 18 completed)
c. ☐ DELETION OF INVENTOR(S)
Signed statement attached deleting
inventor(s) named in the prior application,
see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).

- ☐ Microfiche Computer Program (Appendix)
- ☐ Nucleotide and/or Amino Acid Sequence Submission
(if applicable, all necessary)
a. ☐ Computer Readable Copy
b. ☐ Paper Copy (identical to computer copy)
c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

- ☒ Assignment Papers (cover sheet & document(s))
- ☐ 37 C.F.R. § 3.73(b) Statement (when there is an assignee) ☒ Power of Attorney
- ☐ English Translation Document (if applicable)
- ☐ Information Disclosure Statement (IDS)/PTO-1449 ☐ Copies of IDS Citations
- ☐ Preliminary Amendment
- ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
- ☐ Small Entity Statement(s) ☐ Statement filed in prior application
(PTO/SD/09-12) ☐ Status still proper and desired
- ☐ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
- ☐ Other:

NOTE FOR ITEMS 1 & 2 IN ORDER TO BE ELIGIBLE TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.38)

- If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:
☐ Continuation ☐ Divisional ☒ Continuation-in-part (CIP) of prior application No. **09/427,050**

Prior application information: Examiner: _____ Group / Art Unit: _____
For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

17. CORRESPONDENCE ADDRESS

☐ Customer Number or Bar Code Label

(Insert Customer No. or Attach bar code label here)

or ☒ Correspondence address below

Name	Paul S. Tully				
	Stepan Company				
Address	Intellectual Property Department 22 W. Frontage Road				
City	Northfield	State	IL	Zip Code	60015
Country	USA	Telephone	847-501-2219	Fax	847-446-9359

Name (Print/Type)	Paul S. Tully	Registration No. (Attorney/Agent)	44,377
Signature	<i>Paul Tully</i>	Date	

Burdens Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

10/25/00

09565675 4000000

+

PTO/55/17 (12/99)

Patent and Trademark Office U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no person is required to respond to a collection of information unless it displays a valid OMB control number.

U.S. PRO
9/696675

10/25/00

**FEE TRANSMITTAL
for FY 2000**

Patent fees are subject to annual revision.
Small Entity payments must be supported by a small entity statement,
affidavit or large entity fees must be paid. See Forms PTO/5509-12
and 37 C.F.R. §§ 1.27 and 1.28

TOTAL AMOUNT OF PAYMENT (\$2,130.00)

Complete if Known

Application Number	
Filing Date	October 25, 2000
First Named Inventor	Bric Geiger
Examiner Name	
Group / Art Unit	
Attorney Docket No.	T99.005-B

METHOD OF PAYMENT (check one)

1. ☒ The Commissioner is hereby authorized to charge indicated fees and credit any overpayments to:

Deposit
Account
Number

500904

Deposit
Account
Name

Stepan Company-Paul Tully

- ☒ Charge Any Additional Fee Required
Under 47 C.F.R. § 1.10 and 1.17

2. ☐ Payment Enclosed:

☐ Check ☐ Money Order ☐ Other

FEE CALCULATION

1. BASIC FILING FEE

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
101 600	201 345	Utility filing fee	690.00
100 310	208 155	Design filing fee	
107 480	207 240	Plant filing fee	
108 880	208 345	Reissue filing fee	
114 150	214 75	Provisional filing fee	

SUBTOTAL (1) (\$) 690.00

2. EXTRA CLAIM FEES

Total Claims	Extra Claims	Fee from below	Fee Paid
40	20	18	360
13	3	78	780
		260	260

**or number previously paid, if greater. For Reissues, see below

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description
107 70	202 30	Claims in excess of 20
104 250	204 130	Independent claims in excess of 3
108 78	208 38	Multiple dependent claims, if not paid
110 10	210 8	Reissue independent claims over original patent
		Reissue claims in excess of 20 and over original patent

SUBTOTAL (2) (\$) 1,400.00

FEE CALCULATION (continued)

3. ADDITIONAL FEES

Large Entity Fee Code (\$)	Small Entity Fee Code (\$)	Fee Description	Fee Paid
105 180	205 95	Surcharge - late filing fee or oath	0.00
127 50	227 25	Surcharge - late provisional filing fee or cover sheet	0.00
130 190	230 130	Non-English specification	0.00
147 2,520	247 2,520	For filing a request for reexamination	0.00
112 820	212 920	Requesting publication of SIR prior to Examiner action	0.00
113 1,840	213 1,840	Requesting publication of SIR after Examiner action	0.00
115 110	215 55	Extension for reply within first month	0.00
116 380	216 190	Extension for reply within second month	0.00
117 870	217 435	Extension for reply within third month	0.00
118 1,380	218 690	Extension for reply within fourth month	0.00
128 1,850	228 925	Extension for reply within fifth month	0.00
110 300	210 150	Notice of Appeal	0.00
120 300	220 150	Filing a brief in support of an appeal	0.00
121 260	221 130	Request for oral hearing	0.00
138 1,510	238 1,510	Petition to institute a public use proceeding	0.00
140 110	240 55	Petition to revive - unavoidable	0.00
141 1,210	241 605	Petition to revive - unintentional	0.00
142 1,210	242 605	Utility (oath fee (or statement)	0.00
143 430	243 215	Design (oath fee	0.00
144 580	244 290	Plant (oath fee	0.00
122 130	222 65	Petitions to the Commissioner	0.00
123 50	223 25	Petitions related to provisional applications	0.00
128 240	228 120	Submission of Information Disclosure Sheet	0.00
981 40	681 20	Recording each patent assignment per property (times number of properties)	40.00
145 660	245 330	Filing a submission after final rejection (37 CFR § 1.129(a))	0.00
146 660	246 330	For each additional invention to be examined (37 CFR § 1.129(b))	0.00

Other fee (specify):

Other fee (specify):

Reduced by Basic Filing Fee Paid

SUBTOTAL (3) (\$) 40.00

SUBMITTED BY

Name (Print/Type)

Paul S. Tully

Signature

Paul Tully

Registration No.
(Attorney/Agent)

44,377

Complete if applicable:

Telephone

847-501-2219

Date

10/25/2000

WARNING:

Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO/5509.

Business Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

SCANNED, # 24

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE
(Case No.: T99,005-B)

PATENT

1c921 U.S. PTO
09/696675
10/25/00

In re Application of:)
Eric J. Geiger; Douglas K. Hillshafer)
Serial No.: To Be Assigned)
Filed: Concurrently Herewith)
For: Phthalic Anhydride Based)
Polyester-Ether Polyols And)
Double Metal Cyanide Catalyst)
System For Preparing Same)


CERTIFICATE OF MAILING BY "EXPRESS MAIL"

Assistant Commissioner for Patents
Washington, D.C. 20231
BOX PATENT APPLICATION

Sir or Madam:
"Express Mail" Mailing Label Number: EK323647096US
Date of Deposit: October 25, 2000
Attached Paper or Fee:

1. Declaration for Utility or Design Patent Application (37 CFR 1.63);
2. Copy of continuation in part patent Application, Case No. T99,005-B (52 sheets including cover sheet, claims and abstract);
3. Utility Patent Application Transmittal;
4. Fee Transmittal for FY 2000;
5. Assignment;
6. Recordation Form Cover Sheet
7. Power of Attorney; and
8. PTO Acknowledgement Postcard.

I hereby certify that the attached paper(s) or fee(s) is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" Service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant commissioner for Patents, Patent Application, Washington, D.C. 20231


Karen Ford

SCANNED, # 214

Attachment to PTO/SB/05 (4/98) Utility Patent Application
Transmittal

1. PHTHALIC ANHYDRIDE BASED POLYESTER-ETHER POLYOLS AND DOUBLE METAL CYANIDE CATALYST SYSTEM FOR PREPARING SAME

**APPLICATION FOR UNITED STATES LETTERS PATENT
IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

This application is a Continuation-In-Part of U.S. Patent Application No. 09/427,050, filed October 25,
1999.

(Case No. T99,005-B)

Title: **PHTHALIC ANHYDRIDE BASED POLYESTER-ETHER POLYOLS AND
DOUBLE METAL CYANIDE CATALYST SYSTEM FOR PREPARING
SAME**

Inventors: **Eric J. Geiger; and
Douglas K. Hillshafer,
Both citizens of the United States.**

Assignee: **STEPAN COMPANY, A corporation of the State of Delaware**

Specification

This application is a Continuation-In-Part of U.S. Patent Application No. 09/427,050, filed October 25, 1999.

5

(Case No. T99,005-B)

TO ALL WHOM IT MAY CONCERN:

Be it known that we, Eric J. Geiger, a citizen of the United States and a resident of 31 S. Elm Avenue, Town of Fox Lake, County of Lake, State of Illinois, 60020; and Douglas K. Hillshafer, a
10 citizen of the United States and a resident of 4224 Clausen, Village of Western Springs, County of Cook, State of Illinois, 60558, have invented certain new and useful improvements in

**PHTHALIC ANHYDRIDE BASED POLYESTER-ETHER POLYOLS AND DOUBLE METAL CYANIDE
CATALYST SYSTEM FOR PREPARING SAME**

15

of which the following is a specification.

**PHTHALIC ANHYDRIDE BASED POLYESTER-ETHER POLYOLS AND DOUBLE METAL
CYANIDE CATALYST SYSTEM FOR PREPARING SAME**

(Case # T99,005-B)

5

This application is a Continuation-In-Part of U.S. Patent Application No. 09/427,050, filed October 25, 1999.

BACKGROUND OF THE INVENTION

10

Field of the Invention

15

20

25

Disclosed are polyester-ether polyols and methods for producing such polyester-ether polyols employing a double metal cyanide catalyst, along with urethane prepolymers and methods for producing urethane prepolymers comprising the polyester-ether polyols. Such polyols and urethane prepolymers are useful in the preparation of urethane foams and/or non-foam urethanes, wherein the polyester-ether polyol is either the primary polyol component or is utilized in combination with conventional auxiliary polyester- and/or polyether-based polyols. The invention further relates to urethane foam and non-foam urethane compositions such as coatings, adhesives, sealants, and elastomers, which may be prepared utilizing the polyester-ether polyols and/or the urethane prepolymers derived therefrom. The polyols of the instant invention are preferably the reaction product of phthalic anhydride and diethylene glycol, to produce an intermediate polyester polyol, which is subsequently reacted with an alkylene oxide, e.g., propylene oxide, in the presence of a double metal cyanide catalyst, e.g., a zinc hexacyanometallate and in particular a zinc hexacyanocobaltate, to produce the subject polyester-ether polyols. These polyester-ether polyols impart greatly improved solubility and compatibility to or with mixtures of known alkylene oxide polyols (e.g., polypropylene oxide based polyether polyols) and polyester polyols. The polyester-ether polyols of the instant invention are desirably of lower viscosity than precursor polyester polyols and are generally soluble in either polyester- and/or polyether-based polyols.


Description of the Related Art

30

Desirable physical properties of non-foam polyurethane coatings, adhesives, sealants and elastomers (CASE) include, among others, durability, flexibility, rigidity, hardness, toughness, resistance to abrasion, ability to bond to various substrates, and resistance to chemicals; one of the most desirable properties is hydrolytic stability. Coatings, adhesives, sealants and elastomers which are not resistant to hydrolysis undergo chain scission and gradual degradation of the other physical

properties. Desirable properties of finished urethane foams include beneficial insulation characteristics and flame retardency. Industrial polyurethanes are generally made from the reaction of isocyanates/polyisocyanates and materials with multiple hydroxyl moieties ("polyols"). In many foam, adhesive and coatings formulations, polyols comprise the majority of the formulation weight, so that the final product properties are influenced mostly by the polyols.

Of the commercially available polyols, polyether- and polyester-containing materials are dominant. Polyether polyols are usually based on propylene oxide, ethylene oxide or tetrahydrofuran. These typically exhibit very good resistance to hydrolysis, which is an important requirement of many adhesives and coatings. However, polyether polyols promote adhesion to a very limited variety of substrates. In contrast, polyester polyols generally promote adhesion to more types of surfaces but are more susceptible to hydrolysis. Typically, a polyester molecule is hydrolyzed to an acid and alcohol as shown below. The hydrolysis may be acid or base catalyzed.




The deleterious consequence of such hydrolysis in a polyurethane material is the loss of desirable physical properties, as hydrolysis gives undesirable products with lower molecular weight.

In addition, polyester polyols are utilized in both foam and non-foam formulations to improve physical properties such as toughness, tensile and flexural strength, durometer hardness, solvent resistance, and thermal properties. Urethane coatings, and other applications, based on polypropylene oxide polyols and toluene diisocyanate have found limited applications, i.e. indoors only, as also they contain contaminant ether linkages which are readily prone to oxidative degradation. CASE materials derived from polyester polyols, such as those prepared by the condensation of an aliphatic dicarboxylic acids and poly alcohols, are widely used indoors and outdoors. Their primary function in finished CASE materials has been to enhance abrasion resistance. While these CASE materials possess better durability than those based on polypropylene oxide polyols and toluene diisocyanate, they also contain ether groups that undergo oxidative degradation.

Aliphatic polyester polyols, which contain ether linkages and/or ester linkages have found wide spread use in CASE, as additives which can provide improved bonding and durability. These materials are generally based on caprolactone or adipic acid backbones. One of the more widely

used commercial polyester polyols is based on polycaprolactone and sold under the trade name Tone® (Union Carbide Corp.). This polyester polyol is the product of the homopolymerization of caprolactone with a hydroxyl containing compound as an initiator, such as a diol, to form polycaprolactone polyols. These polyester polyol materials are hydrolytically stable, resistant to yellowing, display excellent abrasion, chemical and impact resistance, they provide excellent resistance to oxidative degradation, and are considered to be the leaders of the commercial products which are currently available. However, such materials are generally of high molecular weight (i.e., 1000 g/mol), they are solids at about 25°C which require heating (to about 60°C) prior to use and they are therefore generally more difficult to formulate with as compared to lower melting, lower viscosity polyols.

Aliphatic polyester polyols based on adipic acid are prepared by the condensation of adipic acid and a diol, such as 1,6-hexanediol, as shown below:



These materials are well known to undergo hydrolytic degradation at the ester linkage sites of the molecule. However, the materials have the advantage of a low manufacturing cost, as compared to Tone® type materials, which is favorable from a consumer point of view.

Polyester polyols derived from phthalic anhydride (PA) and low molecular weight diols are reported in U.S. 4,644,027 to Magnus et al., issued Feb. 17 1987 and U.S. 4,644,047 to Wood, issued Feb. 17, 1987, for the production of cellular polyurethane and polyurethane/polyisocyanurates. Polyester polyols derived from PA and neopentyl glycol have been reported in U.S. 4,390,688 to Walz et al., issued Jun. 28, 1983. These materials are described as water dilutable polyesters with good resistance to xylene and dilute caustic solutions. PA polyester polyols have been used in polyurethane/ polyisocyanurate rigid foams to impart low thermal conductivity, to lower cost and to lower blowing agent usage as reported in U.S. 4,791,148 to Riley et al., issued Dec. 13, 1988; U.S. 4,888, 365 to Riley et al., issued Dec 19, 1989 and U.S. 5,164,422 to Londrigan et al., issued Nov. 17, 1992. The PA based polyester polyols have been used in the preparation of urethane-modified isocyanurate foam as reported in U.S. 4,544,679 to Tideswell et al., issued Oct. 1, 1985.

Rigid foams have incorporated PA-based polyester polyols and perfluorinated hydrocarbons to enhance the thermal insulating properties of the foam, as reported in U.S. 4,981,879 to Snider, issued Jan. 1, 1991 and EP 394736 A2, Snider et al., Oct. 31, 1990. The preparation of urethane prepolymers utilizing conventional polyester and polyether polyols is disclosed in U.S. 5,021,507 to Stanley et al., issued Jun. 4, 1991, and more recently in U.S. 5,863,980 to Choi et al., issued Jan. 26, 1999.

From a preparation perspective, the use of double metal cyanide catalysts in the manufacture of various polyols is well-established in the art. For example, U.S. Pat. No. 3,829,505, assigned to General Tire & Rubber Company, discloses the preparation of high molecular weight diols, triols etc., using these catalysts. The polyols prepared using these catalysts can be fabricated to have a higher molecular weight and a lower amount of end group unsaturation than can be prepared using commonly-used KOH catalysts. The '505 patent discloses that these high molecular weight polyol products are useful in the preparation of nonionic surface active agents, lubricants and coolants, textile sizes, packaging films, as well as in the preparation of solid or flexible polyurethanes by reaction with polyisocyanates. For other double metal cyanide catalyst usage in the polyol context, see for example, U.S. Pat. Nos. 4,985,491 (to Olin Corp., issued Jan. 15, 1991); and 4,77,589 (to Shell Oil Company, issued Oct. 16, 1984).

The polymerization of epoxides such as propylene oxide or mixtures of propylene oxide and ethylene oxide using water and/or alcohols as initiators is also of great industrial importance since the resulting polyether alcohols or polyether polyols are very versatile compounds which can be used as such or as intermediates in the manufacture of various products such as (flexible) polyurethanes, detergents, oil additives and brake fluids.

The polymerization of epoxides is normally carried out under basic conditions, i.e. by using potassium hydroxide or sodium hydroxide as a catalyst. Although products (polyether polyols or polyether alcohols) of good quality can be obtained, the use of these inorganic bases limits the capacity of the process since a long batch time is required to warrant good quality products. Shortening the batch times is not readily achievable by simply using more catalyst, as such increased usage would impose an unacceptable and significant increase in monetary costs. Shortening of the batch time is not however impossible, but it has the intrinsic disadvantage that the selectivity of the process is decreased substantially, which seriously affects the product properties.

Therefore, alternative catalytic systems allowing in principle a shorter batch time have already been proposed in the art. Reference is made in this respect to double metal cyanide complexes such as are disclosed in British Patent Specification No. 1,149,726 (for instance zinc hexacyanometallate complexes also containing zinc chloride, water and an organic ligand) and in East German Patent Specification No. 148,957 (specifically metal hexacyano-iridium complexes also containing zinc chloride, water and an ether).

As mentioned above, both polyester-based and polyether-based polyols have their respective beneficial properties and drawbacks/limitations. Additionally, and perhaps most importantly, polyether and polyester polyols are generally not compatible with each other, i.e., they are often not readily soluble or miscible, and therefore are not readily capable of being employed as a mixture for use in any particular application. An ideal polyol would have the desirable properties exhibited by both ester- and ether-based polyols, with limited disadvantages of each previously mentioned. Additionally, and most importantly, there has been a long felt need for a polyol which can function as either a primary polyol or co-polyol in urethane and urethane prepolymer applications and/or compatibilize, i.e. solubilize, reduce viscosity, and make miscible, mixtures of conventional polyester and polyether polyols.

SUMMARY OF THE INVENTION


This invention relates to novel polyester-ether polyols and their use in preparing urethane prepolymers. Additionally, the invention relates to the use of such polyols and prepolymers in making urethane foams and non-foam urethane coatings, adhesives, sealants and/or elastomers. Methods for producing the polyester-ether polyols are disclosed using double metal cyanide complexes, along with methods for producing urethane prepolymers. It has been surprisingly discovered that the polyester-ether polyols of the instant invention possess highly desirable properties, such as reduced viscosity, improved ease of handling and are highly compatible with ester- and/or ether-based conventional polyols, i.e. they are generally soluble/miscible in either polyester- and/or polyether-based polyols.

The polyester-ether polyols are useful as either the primary polyols in urethane prepolymers, urethane foams and non-foam urethanes, or as a co-polyol in combination with auxiliary conventional ether- and/or ester-based polyols. Additionally, the polyester-ether polyols generally provide improved hydrolytic stability to CASE materials in which they are utilized.

It has been surprisingly discovered that the inventive polyester-ether polyols are soluble in and are compatible with other phthalic and/or non-phthalic anhydride based polyester polyols of similar molecular weights, such as caprolactone based polyester polyols, adipic acid based polyester polyols, terephthalate based polyester polyols, isophthalate based polyester polyols, and other aliphatic based polyester polyols. The polyester-ether polyols of the instant invention provide a unique combination of improved low viscosity and compatibility/compatibilization of polyester and polyether based polyols, which allows for the utilization of the conventional ether- and ester-based polyols in combination with each other. The polyester-ether polyols of the instant invention allow for the formation of stable and compatibilized mixtures of ester- and ether-based polyols which are usually immiscible.

DETAILED DESCRIPTION OF THE INVENTION

The polyester-ether polyols of the present invention are generally the reaction product of phthalic anhydride (PA), a polyhydroxyl compound, and an alkoxyating agent, e.g., propylene oxide, as shown below:




wherein R is branched or linear, saturated or unsaturated C₂₋₁₀ alkyl, cycloalkyl, alkenyl, alkynyl, aromatic, polyoxyethylenic, polyoxypropylenic; wherein R may contain pendant secondary functionality such as hydroxyl, aldehyde, ketone, ether, ester, amide, nitrile, amine, nitro, thiol, sulfonate, sulfate, and/or carboxylic groups; n is typically 1- 200 and each n1 is independently 1 –

200. Where pendant secondary hydroxyl functionality is present, such hydroxyl groups may optionally be alkoxyated. Preferably, phthalic anhydride is reacted with a polyol, i.e., a diol such as diethylene glycol to form an intermediate polyester polyol.

The intermediate polyester polyol is then reacted with an alkoxyating agent, such as propylene oxide, to form the polyester-ether polyol. Although traditional catalysts, such as sodium hydroxide have proven useful to effectuate the alkoxylation, it has been surprisingly discovered that the alkoxylation reaction can be more efficiently conducted using a double metal cyanide catalyst. Without wishing to be bound by any particular theory, it is speculated that unsaturated end groups result in monofunctional species that act as chain stoppers/terminators in elastomer/polymer formation, whereby such formation is highly undesirable. In typical polyol synthesis with KOH catalysis the unsaturation formed increases as a direct function of equivalent weight. Eventually conditions are established wherein further alkylene oxide, e.g., propylene oxide, addition fails to increase the molecular weight. In other words the use of alkali catalysts to produce high molecular weight, hydroxy terminated polyoxypropylene ethers typically results in a substantial loss in hydroxy functionality. It has been discovered that with double metal cyanide catalysis much less unsaturation is formed allowing higher equivalent weight polyester ether polyols to be prepared.

The double metal cyanide complex class catalysts suitable for use herein and their preparation are described in U.S. Pat. Nos. 4,472,560 and 4,477,589 to Shell Chemical Company and U.S. Pat. Nos. 3,941,849 and 4,335,188 to General Tire & Rubber Company. The teachings of the foregoing patents are incorporated herein by reference.

One class of double metal cyanide complex catalysts found particularly suitable for use herein is are zinc hexacyanometallates of the general formula:




wherein M may be Co(III), or Cr(III) or Fe(II) or Fe(III); x, y, and z may be fractional numbers, integers, or zero and vary depending on the exact method of preparation of the complex. Also useful is a zinc hexacyanometallates of the general formula:



wherein M is defined as above.

A highly preferred double metal cyanide complex catalyst found particularly suitable for use is a zinc hexacyanometallate of formula:




as described in J. Catal (105) 163-174, 1987 by Kuyper and Boxhoorn, including its preparation, incorporated herein by reference in its entirety.

Other suitable catalysts include general formula:



wherein M^1 represents at least one of Zn(II), Fe(II), Co(II), Ni(II), Mn(II), Cu(II), Sn(II) or Pb(II); M^2 represents at least one of Fe(II), Fe(III), Co(III), Cr(III), Mn(II), Mn(III), Ir(III), Rh(III), Ru(II), V(IV) or V(V); M^3 represents M^1 and/or M^2 ; A, D and E each represent an anion which may be the same or different; L represents an alcohol, aldehyde, acetone, ether, ester, amide, nitrile or sulphide or mixtures thereof; a and d are numbers to satisfy the valency state of M^1 and M^2 in the double metal cyanide part of the general formula I; b and c are integers ($b > c$) which together with a and d provide the electroneutrality of the double metal cyanide part of the general formula I; e is an integer satisfying the valency state of M^3 ; n and m are integers satisfying the electroneutrality of HE, and w is a number between 0.1 and 4; x is a number up to 20; y is a number between 0.1 and 6, and z is a number between 0.1 and 5.

Other useful catalysts include zinc hexacyano cobaltates according to the general formula:



wherein X represents a halide; M^3 represents Zn(II), Co(II) or Fe(II); L represents an alcohol, ether or ester and w is a number between 0.7 and 1.5; x is a number between 2 and 10; y is a number between 1.5 and 3, and z is a number between 0.15 and 1.5.


In accordance with this formula and the above formula, L can be an alcohol, aldehyde, ketone, ether, ester, amide, nitrile or sulphide. Examples of alcohols include lower alcohols such as methanol, ethanol, propanol, isopropanol and butanol. Higher alcohols as well as alcohols containing aromatic rings can also be used. Examples of aldehydes include formaldehyde, acetaldehyde, butyraldehyde, pivalaldehyde, glyoxal, benzaldehyde and cinnamic aldehyde. Examples of ketones include acetone, methyl ethyl ketone, methyl isobutyl ketone, diethyl ketone and cyclohexanone. Examples of ethers include monoethers, diethers and polyethers as well as cyclic ethers such as dimethyl ether, diethyl ether, dibutyl ether, methyl t-butyl ether, bis-(beta-methoxy ethyl) ether, ethylene glycol dimethyl ether, triethylene glycol dimethyl ether, dimethoxy methane, diethoxy methane, acetal, trimethylol propane trimethyl ether, dioxane, trioxyethylene and paraldehyde.

Preference is given to the use of acyclic ethers, in particular acyclic diethers such as dimethoxy ethane (ethylene glycol dimethyl ether). Also hydroxy ethers such as ethylene glycol monomethyl ether and related compounds can be used conveniently. Examples of esters include methyl formate, ethyl formate isopropyl formate, methyl acetate, ethyl acetate, propyl acetate, ethylene glycol diacetate and triethylene glycol diacetate. Examples of amides include formamide, acetamide, propionamide, valeramide as well as urea and derivatives thereof. Examples of nitriles include acetonitrile, propionitrile and valeronitrile. Examples of sulphides include dimethyl sulphide, diethyl sulphide and ethyl butyl sulphide. Also mixtures of two or more organic compounds can be applied.

The acids according to the general formula H_nE_m which are present in the double metal cyanides comprise hydrochloric acid, hydrobromic acid, hydroiodic acid, nitric acid, sulphuric acid, phosphoric acid, (per)chloric acid, carboxylic acids such as acetic acid and benzoic acid, halogen-substituted carboxylic acids such as trichloro acetic acid and trifluoro acetic acid, alkyl sulphonic acids and aryl sulphonic acids such as methane sulphonic acid and para-toluene sulphonic acid. Preference is given to the hydrogen halides and sulphuric acid, and particularly hydrogen chloride and hydrogen bromide. Mixtures of acids can also be used suitably.

The present invention relates to a process for the preparation of polyester-ether polyols which comprises alkoxylating at least one polyester polyol compound in the presence of at least one alkoxylating agent, in the presence of at least one double metal cyanide complex catalyst as disclosed above. The present invention further relates to the polyester-ether polyols produced by the above process.

While a wide variety of polyhydric alcohols may be utilized in the present invention to prepare the intermediate polyester polyols, preferred PA polyester polyol intermediates are of the form



wherein $n = 2-10$, $x = 1-500$. Highly preferred PA polyester polyol intermediates for use in the present invention are derived from the condensation of phthalic anhydride and ethylene glycol, diethylene glycol, propylene glycol, dipropylene glycol, neopentyl glycol, 1,4-butanediol, 1,6-hexanediol,

polyethylene glycol, polypropylene glycol triethylene glycol, and tetramethylene glycol and mixtures thereof.

Alkoxylating agents useful herein include any agent capable of providing a sufficient amount of ether moieties to the final polyester-ether polyol. Preferred alkoxylating agents are ethylene oxide, propylene oxide, butylene oxide, or mixtures thereof.

The phthalic anhydride based polyester-ether polyols are compatible with standard foam flowing and formation techniques and are also compatible with atmospheric curing, heat curing, and exhibit normal pigmentation compatibility.

The invention encompasses polyester-ether polyols, methods for preparing such polyols, and their use in preparing urethane prepolymers, urethane foams and non-foam urethane coatings, adhesives, sealants and/or elastomers. The polyester-ether polyols of the instant invention are preferably the reaction product of phthalic anhydride or phthalic acid, a diol, and an alkoxylating agent, wherein the phthalic anhydride or phthalic acid and the diol are first reacted to form an intermediate polyester polyol, which is subsequently reacted with an alkoxylating agent (e.g., propylene oxide), to give a polyester-ether polyol. Although the polyester-ether polyols of the instant invention are useful as the primary polyols in the preparation of urethane prepolymers, urethane foams and CASE materials, they are primarily and preferably useful as compatibilizing polyols in combination with polyester and/or polyether polyols.


Accordingly, the instant invention encompasses a composition suitable for preparing urethane prepolymers and/or urethane foams or non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising:

(a) from about 0 % to about 5.0 % based on the weight of the composition of a urethane catalyst;

(b) from about 10% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:

(1) about 2 - 60 % based on the weight of the polyester-ether polyol of phthalic anhydride or phthalic acid; and

(2) about 40 - 98 % based on the weight of the polyester-ether polyol of at least one polyol of the formula:




wherein R₁ represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) -CH₂-R₂-CH₂-

where R₂ represents:



(c) -(R₃O)_{n2}-R₃-

where each R₃ independently is an alkylene group of about 2 to about 4

carbon atoms, and n2 is an integer of from about 1 - 200; and

10 (3) about 10 – 80 % based on the weight of the polyester-ether polyol of an alkoxyating agent;

(c) from about 0 - 50 percent by weight of an auxiliary polyether polyol, polyester polyol, or a mixture thereof;

15 (d) from about 0% to about 10% based on the weight of the composition of a blowing agent; and

(e) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant.

The R₁ alkylene groups may be branched or straight chain, saturated or unsaturated, and when R₂ contains a hydroxyl moiety, such hydroxyl group may be optionally alkoxyated. The polyester-ether polyol is preferably the reaction product of phthalic anhydride or phthalic acid, the polyol, and the alkoxyating agent, wherein the phthalic anhydride or phthalic acid and the polyol are first reacted to form an intermediate polyester polyol, which is subsequently reacted with the alkoxyating agent to give the polyester-ether polyol.

20


The instant invention further encompasses a composition suitable for preparing urethane prepolymers and/or urethane foams or non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising:

25

(a) from about 10 % to about 60% based on the weight of the composition of an isocyanate;

(b) from about 50% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:


- (1) about 2 - 60 % based on the weight of the polyester-ether polyol of phthalic anhydride or phthalic acid; and
- (2) about 40 - 98 % based on the weight of the polyester-ether polyol of at least one polyol of the formula:



wherein R₁ represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) -CH₂-R₂-CH₂-

where R₂ represents:



- (c) -(R₃O)_{n2}-R₃-

where each R₃ independently is an alkylene group of about 2 to about 4 carbon atoms, and n₂ is an integer of from about 1 - 200; and

- (3) about 10 - 80 % based on the weight of the polyester-ether polyol of an alkoxyating agent.

(c) from about 0 - 50 % based on the weight of the composition of an auxiliary polyether polyol, polyester polyol, or a mixture thereof;

(d) from about 0% to about 10% based on the weight of the composition of a blowing agent; and

(e) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant.

The R alkylene groups may be branched or straight chain, saturated or unsaturated, and when R₂ contains a hydroxyl moiety, such hydroxyl group may be optionally alkoxyated. The polyester-ether polyol is preferably the reaction product of phthalic anhydride or phthalic acid, the polyol, and the alkoxyating agent, wherein the phthalic anhydride or phthalic acid and the polyol are first reacted to

from an intermediate polyester polyol, which is subsequently reacted with the alkoxylating agent to give the polyester-ether polyol.

Most commonly when a urethane prepolymer is desired, it is prepared by condensation polymerization, i.e., the isocyanate with the polyol(s), most preferably the polymerization of a diisocyanate with a diol. A prepolymer is generally defined as a non-stoichiometric reaction product of an isocyanate and a polyol. The urethane prepolymers may also be prepared by polymerizing the compositions disclosed herein in the presence of an optional polyamino or a polymercapto-containing compound such as diamino polypropylene glycol or diamino polyethylene glycol or polythioethers such as the condensation products of thiodiglycol either alone or in combination with other glycols such as ethylene glycol, 1,2-propylene glycol or with other polyhydroxy compounds disclosed herein. Also, small amounts of low molecular weight dihydroxy, diamino, or amino hydroxy compounds may be used such as saturated and unsaturated glycols e.g. ethylene glycol or condensates thereof such as diethylene glycol, triethylene glycol, and the like; ethylene diamine, hexamethylene diamine and the like; ethanolamine, propanolamine, N-methyldiethanolamine and the like. Typically for the preparation of urethane prepolymers, the isocyanate, polyol(s), and other components are combined in proportions so as to yield a urethane prepolymer characterized by an isocyanate content of from about 0.25 to about 25%, preferably to about 1 to 10%, and most preferably from 1.5 to 5%. In addition, the ratio of isocyanate equivalents to hydroxyl, amino or mercapto equivalents (known as the isocyanate index) should be greater than 1 but no more than about 2 for prepolymer preparation. The precise amount of the isocyanate used in the polymerization will depend on the equivalent weight and amount of the non-isocyanate components, and the particular isocyanate employed. In general, the amount of the isocyanate needed to achieve the isocyanate content will vary from about 5 to about 55% of the final prepolymer.


The invention further encompasses a composition suitable for preparing urethane prepolymers and/or urethane foams or non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising:

- (a) from about 10 % to about 70% based on the weight of the composition of an isocyanate;
- (b) from about 0.02 % to about 5.0 % based on the weight of the composition of a urethane catalyst; and

(c) from about 50% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:

(1) about 2 - 60 % based on the weight of the polyester-ether polyol of phthalic anhydride or phthalic acid; and

(2) about 40 - 98 % based on the weight of the polyester-ether polyol of at least one polyol of the formula:




wherein R_1 represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) $-\text{CH}_2\text{-R}_2\text{-CH}_2-$

where R_2 represents:



(c) $-(\text{R}_3\text{O})_{n2}\text{-R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and $n2$ is an integer of from about 1 - 200; and

(3) about 10 - 80 % based on the weight of the polyester-ether polyol of an alkoxylating agent selected from the group consisting essentially of ethylene oxide, propylene oxide or butylene oxide or mixtures thereof;

(d) from about 0 - 50 % based on the weight of the composition of an auxiliary polyether polyol, polyester polyol, or a mixture thereof.

(e) from about 0% to about 10% based on the weight of the composition of a blowing agent; and

(f) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant.

The R_1 alkylene groups may be branched or straight chain, saturated or unsaturated, and when R_2 contains a hydroxyl moiety, such hydroxyl group may be optionally alkoxylated. The polyester-ether polyol is preferably the reaction product of phthalic anhydride or phthalic acid, the polyol, and the


alkoxylating agent, wherein the phthalic anhydride or phthalic acid and the polyol are first reacted to from an intermediate polyester polyol, which is subsequently reacted with the alkoxylating agent to give the polyester-ether polyol.

In a more preferred embodiment the compositions suitable for preparing urethane prepolymer and/or urethane foams and non-foam urethane coatings, adhesives, sealants and/or elastomers will comprise from about 10 - 40 %, most preferably from about 10 - 30 % of the isocyanate when present; from about 0.5 - 4.0 %, most preferably from about 0.5 - 3.0 % of the urethane catalyst when present; from about 50 - 80 %, most preferably from about 50 - 70 % of the phthalate polyester-ether polyol, wherein the phthalate polyester-ether polyol preferably comprises from about 10 - 60 %, most preferably 20 - 50 % of phthalic acid or phthalic anhydride; preferably from about 40 - 80 % of the polyol; and preferably from about 10 - 50 % of the alkoxylating agent. In highly preferred embodiments, the alkoxylating agent is propylene oxide and is present in about 50-60 % by weight, based on the intermediate polyester polyol. In a more preferred embodiment the urethane prepolymers and/or urethane compositions will comprise from about 5 - 40 %, most preferably from about 10 - 30 % of the auxiliary polyether polyol, polyester polyol, or a mixture thereof.

The compositions disclosed herein may be substantially free of CFC and/or hydrocarbon blowing agents (i.e. they contain less than 1% by weight of a blowing agent) and are suited for use in non-foam applications, i.e., CASE. Alternatively, the compositions of the present invention may optionally contain CFC and/or hydrocarbon blowing agents and be suited for use in foam applications, i.e., open and closed cell foams. Optionally, the composition disclosed herein may additionally contain from about 0.01 - 20.0 % by weight of a polyisocyanurate.

In a preferred embodiment, the alkoxylating agent is propylene oxide. Highly preferred isocyanates are 2,4- and/or 2,4,2,6-toluene diisocyanate, diphenyl methane 4,4'-diisocyanate, hexamethylene diisocyanate, isophorone diisocyanate, or mixtures thereof. Highly preferred urethane catalysts are tetramethylbutanediamine (TMEDA), 1,4-diaza(2,2,2)bicyclooctane (DABCO), dibutyltin dilaurate (DBTDL) tin octoate (SnOct), dimorpholine diethylether (DMDEE), or mixtures thereof.

A preferred polyester-ether polyol for use in the above and below described compositions has the formula:




wherein R represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

5

where R_2 represents:



- (c) $-(\text{R}_3\text{O})_{n_2}-\text{R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and n_2 is an integer of from about 1 - 200; and


10

wherein R' and R'' are independently $-\text{[CH}_2\text{CH}_2\text{O]}_{n_1}-$, $-\text{[CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n_1}-$, $-\text{[CH}_2\text{CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n_1}-$, or a random combination thereof, where n_1 is independently 1-200 for R' and R'' ; and wherein n is 1 - 200.

The R alkylene groups may be branched or straight chain, saturated or unsaturated, and when R_2 contains a hydroxyl moiety, such hydroxyl group may be optionally alkoxylated.

15



A highly preferred polyester-ether polyol has the formula



wherein R represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R₂ represents:




where each R₃ independently is an alkylene group of about 2 to about 4 carbon atoms, and

n₂ is an integer of from about 1 - 200; and

where n₁ is independently 1-200; and wherein n is 1 - 200.

The R alkylene groups may be branched or straight chain, saturated or unsaturated, and when R₂ contains a hydroxyl moiety, such hydroxyl group may be optionally alkoxylated.

A most preferred polyester-ether polyol has the formula



wherein each R is $-(\text{CH}_2\text{CH}_2\text{OCH}_2\text{CH}_2)-$; wherein each n₁ is independently 1-200; and

wherein n = 1 - 200.

Specific auxiliary polyester polyols suitable for use in the compositions of the invention include for example phthalic acid diethylene glycol polyester polyols. Suitable auxiliary phthalic acid diethylene glycol polyester polyols are commercially available from Stepan Company, Northfield, Illinois. Representative auxiliary polyols are StepanPol® PS-2002 (a phthalic anhydride diethylene glycol polyester polyol having an OHv of 195 and a functionality of 2), StepanPol® PS-3152 (a phthalic anhydride diethylene glycol polyester polyol having an OHv of 315 and a functionality of 2), and StepanPol® PS-4002 (a phthalic anhydride diethylene glycol polyester polyol having an OHv of 400 and a functionality of 2), and mixtures thereof. In the instant invention, by OH value (OHv) is meant hydroxyl value, a quantitative measure of the concentration of hydroxyl groups, usually stated as mg KOH/g, i.e., the number of milligrams of potassium hydroxide equivalent to the hydroxyl groups

in 1 g of substance. By functionality is meant the number of reactive groups, e.g., hydroxyl groups, in a chemical molecule.

Other auxiliary polyester polyols, i.e. non-phthalic anhydride-based polyester polyols, include for example, polyester polyols derived from the condensation of caprolactone and a poly alcohol. Specific auxiliary polyether polyols suitable for use in the methods and compositions of the invention include for example the condensation products of propylene glycol/propylene oxide, trimethylolpropane/ethylene oxide/propylene oxide, trimethylolpropane/propylene oxide, sucrose/propylene glycol/propylene oxide, alkylamine/propylene oxide, and glycerin/propylene oxide, and mixtures thereof.

Although not critical to the present invention, the compositions of the present invention may optionally contain from about 0.01 - 50.0 percent by weight of a cross linking agent. Suitable cross linking agents are, for example, higher functionality alcohols such as triols or pentaerythritol.

A wide variety of urethane catalysts are suitable for use in the present invention. Generally, any urethane catalyst capable of effecting a polymerization to form a urethane CASE may be used in the present invention. Examples of suitable urethane catalysts include, among others, tetramethylbutanediamine (TMBDA), 1,4-diaza(2,2,2)bicyclooctane (DABCO), dibutyltin dilaurate (DBTDL) and tin octoate (SnOct), and mixtures thereof.

Isocyanates useful in the present invention, include among others for example, polyisocyanates, aliphatic, cycloaliphatic, araliphatic, aromatic and heterocyclic polyisocyanates, such as those described, for example, by W. Siefken in Justus Liebigs Annalen der Chemie 562: 75-136. Examples include ethylene diisocyanate; tetramethylene-1,4-diisocyanate, hexamethylene-1,6-diisocyanate; dodecane-1,12-diisocyanate; cyclobutane-1,3-diisocyanate; cyclohexane-1,3- and 1,4-diisocyanate and mixtures of these isomers; 1-isocyanato-3,3,5-trimethyl-5-isocyanatomethylcyclohexane (German Auslegeschrift No. 1, 202,785, U.S. Pat. No. 3,401,190); hexahydrotolylene-2,4- and 2,6-diisocyanate and mixtures of these isomers; hexahydrophenylene-1,3- and/or -1,4-diisocyanate; perhydrodiphenylmethane-2,4'- and/or 4,4'-diisocyanate; phenylene-1,3- and -1,4-diisocyanate; toluene-2,4- and -2,6-diisocyanate and mixtures of these isomers; diphenylmethane-2,4'- and/or -4,4'-diisocyanate; naphthylene-1,5-diisocyanate; triphenyl methane-4,4',4"-triisocyanate; polyphenyl-polymethylene polyisocyanate which may be obtained by aniline/formaldehyde condensation followed by phosgenation and which have been described, for

example, in British Pat. Nos. 874,430 and 848,671; m-and p-isocyanatophenyl sulphonyl isocyanate according to U.S. Pat. No. 3,454,606; perchlorinated aryl polyisocyanate as described, for example, in U.S. Pat. No.3,277,138; polyisocyanate; containing carbodiimide groups as described in U.S. Pat. No. 3,152,162; the diisocyanates described in U.S. Pat. No. 3,492,330; polyisocyanates containing allophanate groups as described, for example, in British Pat. No. 994,890, Belgian Pat. No. 761, 626 and Published Dutch Patent application No. 7,102, 524; polyisocyanates containing isocyanurate groups as described, for example, in U.S. Pat. No. 3,001,973, in German Pat. Nos. 1,022,789; 1,222,067 and 1,027,394 and in German Offenlegungsschriften Nos. 1,929,034 and 2,004,048; polyisocyanates containing urethane groups as described, for example, in Belgian Pat. No. 752,261 or in U.S. Pat. No. 3,394,164; polyisocyanates containing acrylated urea groups according to German Pat. No. 1,230,778; polyisocyanates containing biuret groups as described, for example, in U.S. Pat. Nos. 3,124,605 and 3, 201,372; and in British Pat. No. 889,050; polyisocyanates prepared by telomerization reactions as described, for example in U.S. Pat. No. 3,654,016; polyisocyanates containing ester groups as mentioned, for example, in British Pat. Nos. 965,474 and 1,072,956, in U.S. Pat. No. 3, 567,763 and in German Pat. No. 1,231,688; reaction products of the above-mentioned isocyanates with acetals according to German Pat. No. 1,072,385; and, polyisocyanates containing polymeric fatty acid groups as described in U.S. Pat. No. 3,455,883, and mixtures thereof.

The distillation residues obtained from the commercial production of isocyanates and which still contain isocyanate groups may also be used, optionally dissolved in one or more of the above-mentioned polyisocyanates.


Other suitable polyisocyanates which are readily available include, for example, toluene-2,4- and -2,6-diisocyanate and mixtures of these isomers ("TDI"); polyphenyl polymethylene polyisocyanates which may be obtained by aniline/formaldehyde condensation followed by phosgenation ("crude MDI"); and, polyisocyanates containing carbodiimide groups, urethane groups, allophanate groups, isocyanurate groups, urea groups or biuret groups ("modified polyisocyanates"), and mixtures thereof.

Somewhat more preferred polyisocyanates are 2,4- and/or 2,4/2,6-toluene diisocyanate, diphenyl methane 4,4'-diisocyanate, hexamethylene diisocyanate, and isophorone diisocyanate, and mixtures thereof.

Suitable polyisocyanurates useful in the present invention also include, as is well known to those skilled in the art, the cyclotrimerization product of any of the aforementioned polyisocyanates.

Compositions of the present invention may contain optional ingredients, including for example, rheology modifiers, plasticizers, pigments, and waxes.

Another embodiment of the present invention includes a novel polyester-ether polyol for use in preparing urethane prepolymers, urethane foams and non-urethane coatings, sealants, adhesives and/or elastomers of the formula:




wherein R represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R_2 represents:



(c) $-(\text{R}_3\text{O})_{n2}-\text{R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and


$n2$ is an integer of from about 1 - 200; and

where $n1$ is independently 1-200; and

wherein n is 1 - 200.

The R alkylene groups may be branched or straight chain, saturated or unsaturated, and when R_2 contains a hydroxyl moiety, such hydroxyl group may be optionally alkoxyated.

Another embodiment of the present invention includes a novel polyester-ether polyol for use in preparing urethane prepolymers, urethane foams and non-urethane coatings, sealants, adhesives and/or elastomers of the formula:




wherein each R is $-(CH_2CH_2OCH_2CH_2)-$; wherein each n_1 is independently 1-200; and

wherein $n = 1 - 200$.

The instant invention further includes methods for preparing a phthalate polyester-ether polyol comprising combining:


- about 2 - 60 % based on the weight of phthalate polyester-ether polyol of phthalic anhydride or phthalic acid; and
- about 40 - 98 % based on the weight of phthalate polyester-ether polyol of at least one polyol of the formula:



wherein R_1 represents:

- alkylene groups of about 2 to 10 carbon atoms;
- $-CH_2-R_2-CH_2-$

where R_2 represents:



- $-(R_3O)_{n_2}-R_3-$


where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and n_2 is an integer of from about 1 - 200,

to form an intermediate polyester-polyol; and alkoxyating said intermediate polyester polyol with about 10 - 80 % based on the weight of the phthalate polyester-ether polyol of an alkoxyating agent to form the polyester-ether polyol. The R_1 alkylene groups may be branched or straight chain, saturated or unsaturated, and when R_2 contains a hydroxyl moiety, such hydroxyl group may be


optionally alkoxylation. Further in accordance with this method embodiment, the alkoxylation may be conducted in the presence of a double metal cyanide complex catalyst. The double metal cyanide complex catalyst may be of the formula



wherein M^1 represents at least one of Zn(II), Fe(II), Co(II), Ni(II), Mn(II), Cu(II), Sn(II) or Pb(II); M^2 represents at least one of Fe(II), Fe(III), Co(III), Cr(III), Mn(II), Mn(III), Ir(III), Rh(III), Ru(II), V(IV) or V(V); M^3 represents M^1 and/or M^2 ; A, D and E each represent an anion which may be the same or different; L represents an alcohol, aldehyde, acetone, ether, ester, amide, nitrile or sulphide or mixtures thereof; a and d are numbers to satisfy the valency state of M^1 and M^2 in the double metal cyanide part of the general formula I; b and c are integers ($b > c$) which together with a and d provide the electroneutrality of the double metal cyanide part of the general formula I; e is an integer satisfying the valency state of M^3 ; n and m are integers satisfying the electroneutrality of HE, and w is a number between 0.1 and 4; x is a number up to 20; y is a number between 0.1 and 6, and z is a number between 0.1 and 5. Alternatively, the double metal cyanide complex catalyst may be of the formula



wherein X represents a halide; M^3 represents Zn(II), Co(II) or Fe(II); L represents an alcohol, ether or ester and w is a number between 0.7 and 1.5; x is a number between 2 and 10; y is a number between 1.5 and 3, and z is a number between 0.15 and 1.5. In yet another embodiment, the double metal cyanide complex catalyst is of the formula



Combinations of the various metal catalysts may optionally be used. Additionally, the invention relates to a polyester-ether polyols produced by the above methods using the metal catalysts disclosed.

The instant invention further includes methods for preparing urethane prepolymers, urethane foams and non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising combining:


(a) from about 10 % to about 60% based on the weight of the composition of an isocyanate;

(b) from about 0.02 % to about 5.0 % based on the weight of the composition of a urethane catalyst; and

(c) from about 50% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:

(1) about 2 - 60 % based on the weight of phthalate polyester-ether polyol of phthalic anhydride or phthalic acid; and

(2) about 40 - 98 % based on the weight of phthalate polyester-ether polyol of at least one polyol of the formula:




wherein R₁ represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) -CH₂-R₂-CH₂-

where R₂ represents:



(c) -(R₃O)_{n2}-R₃-

where each R₃ independently is an alkylene group of about 2 to about 4 carbon atoms, and n2 is an integer of from about 1 - 200; and

(3) about 10 - 80 % based on the weight of phthalate polyester-ether polyol of an alkoxyating agent; and

(d) from about 0 - 50 % based on the weight of the composition of an auxiliary polyether polyol, polyester polyol, or a mixture thereof;

(e) from about 0% to about 10% based on the weight of the composition of a blowing agent;

(f) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant,

to form a mixture; and

reacting/polymerizing the mixture to form a urethane prepolymer, urethane foam or non-foam urethane coating, adhesive, sealant and/or elastomer. The polyester-ether polyol is preferably the reaction product of phthalic anhydride or phthalic acid, the polyol, and the alkoxyating agent, wherein

the phthalic anhydride or phthalic acid and the polyol are first reacted to form an intermediate polyester polyol, which is subsequently reacted with the alkoxyating agent to give the polyester-ether polyol.

Another embodiment of the present invention includes urethane prepolymers, urethane foams and non-foam urethanes suitable for use in a coatings, adhesives, sealants and/or elastomers which are made from polymerizing the compositions suitable for preparing such materials as described herein.

The merits of this invention are further supported by the following non-limiting and illustrative examples.

EXAMPLES

As used in the Examples and description appearing below, the following designations, symbols, terms and abbreviations have the indicated meanings:

<u>Material</u>	<u>Description</u>
STEPANPOL® PS-2002	~200 OHv; phthalic anhydride/diethylene glycol polyester; Acid Number = 0.64
TONE 0201	~200 OHv; polycaprolactone glycol; Acid Number = 0.13
Formrez® 11-225	~200 OHv; diethylene glycol/adipic acid polyester glycol
"Liquid" MDI	methylene-diphenylene isocyanate
Voranol 220-056N	The product of propoxylation of propylene glycol to an approximate hydroxyl value of 56.1 mg KOH/g. Residual potassium, the catalyst for the propoxylation at ca. 0.2% by weight of the final product, is typically removed by adsorption of potassium on magnesium silicate which is in turn removed from the product by filtration. About 50 ppm (parts per million) of phosphoric acid are then added to the final polypropylene glycol to assure the product is not basic.
Voranol 220-110	Voranol 220-110N with no addition of phosphoric acid
Magnesol	Magnesium silicate; manufactured by the Dallas Group of Indiana; a hydrated, synthetic, amorphous magnesium silicate with a porous structure and active surface that imparts high performance, selective, and sorptive properties; its highly active surface attracts sodium, potassium, and other metal ions as well as other polar compounds by chemisorption and holds them for removal from the process by filtration

In the following examples, all amounts are stated in percent by weight of active material unless indicated otherwise. One skilled in the art will recognize that modifications may be made in the present invention without deviating from the spirit or scope of the invention. The invention is illustrated by the examples contained within; such examples are not to be construed as limiting the invention or scope of the specific procedures or compositions described herein.

The following raw materials in Table I were used without purification in the examples which follow (abbreviations used are PA = phthalic anhydride, DEG = diethylene glycol, PPG = polypropylene glycol, PPO = polypropylene oxide, Gyl = glycerin, Su = sucrose, OHv = hydroxyl value in mg KOH/g) . Polyols A and B are commercially available polyester polyols used as comparative examples as indicated below.

Table I

Designation	Product Name	Supplier	Description
Polyol A	Voranol 220-056N	Dow USA	55.7 mg KOH/g OHv PPG
Polyol B	Voranol 220-110	Dow USA	108.9 mg KOH/g OHv PPG
Isocyanate	Mondur M, Flaked	Bayer	4,4'-diphenylmethane diisocyanate
DBTDL	Dibutyl tin dilaurate	Air Products	Organotin catalyst
Extender	1,4-butane diol	Air Products	Chain extender glycol

As shown in Table II, polyol C (comparative example) is a standard PA-DEG polyol (StepanPol PS-2002) and polyols D and E are examples of polyester-ether polyols. Both these polyols were prepared by the propoxylation of a *ortho*-phthalate diethylene glycol ester (StepanPol PS-2002).

Table II

Designation	Description
Polyol C	52.5 mg KOH/g OHv PA-DEG glycol
Polyol D	62 mg KOH/g OHv PA-DEG-propoxylate
Polyol E	87 mg KOH/g OHv PA-DEG-propoxylate

Example 1: Preparation of Polyester Polyol C (comparative example; STEPANPOL[®] PS-2002)

PS-2002 is prepared as the condensation product of about 45% diethylene glycol (DEG) and 55% phthalic anhydride. Into a three gallon kettle is charged 4500 g of DEG and 5500 g PA. This

mixture is heated to about 180°C for four hours under a nitrogen atmosphere. After four hours the temperature is raised to about 180 - 200°C, and approximately 500 ppm of catalyst tetrabutyl titanate (Tyzor TBT, DuPont) is added to the kettle. The pressure is reduced in the kettle and removal the water by-product is begun under vacuum. The water is completely removed after about 24 hours of reaction at about 180 - 200°C under vacuum. The final polyester polyol is characterized by a hydroxyl number of 190 - 200 mg KOH/g and has a Brookfield viscosity of about 20,000 - 30,000 cPs at 25°C and an acid value less than 1 mg KOH/g.

Example 2: Preparation of Polyester-Ether Polyol D (propoxylated *ortho*-phthalate diethylene glycol ester)

Into a two gallon steel pressure Chemineer kettle is charged 3678 grams StepanPol® PS-2002 and 155 grams of crushed potassium hydroxide. The mixture is blended under a nitrogen blanket for 2 hours at 120°C. A total of 7,060 grams of propylene oxide is added under a pressure of <42 psig over three hours at a temperature of about 120 - 125°C. A total of 500 grams of this crude product is then transferred to a flask where it is then heated to about 100°C and degassed to remove unreacted propylene oxide. The material is then finished/neutralized: To the remaining warm mixture, 1.5 grams of Magnesol HMR-LS (The Dallas Group) is added and the mixture is then stirred at about 100 - 120°C for four hours. The resulting mixture is allowed to stand warm (80°C) for approximately 12 hours and the product is decanted and filtered through a vacuum flask equipped with a Buchner funnel and a #4 Whatman filter paper. Approximately 0.1 % H₃PO₄ (85 %) by weight of the polyol is then added. Analysis of polyol D gave the following properties:

OH value = 87 mg KOH/g (ASTM E 222 method)

Dynamic viscosity = 1,200 cP @ 25°C (Brookfield, #31 spindle)

% moisture = 0.068% (ASTM D 4672 method)

% Propylene oxide = 55% by weight

Example 3: Preparation of Polyester-Ether Polyol E (propoxylated *ortho*-phthalate diethylene glycol ester)

Polyol E is prepared in a similar manner to that of polyol D, except the amounts of materials used are 14.5 g KOH, 2890 g, StepanPol PS-2002 and 6010 g propylene oxide. Analysis of polyol E gave the following properties:

OH value = 59.4 mg KOH/g (ASTM E 222 method)

Dynamic viscosity = 1,400 cP @ 25°C (Brookfield, #31 spindle)

% Propylene oxide = 69% by weight

% Moisture = 0.023% (ASTM D 4672 method)

5

Example 4: Preparation of Polyester-Ether Polyol F (propoxylated *ortho*-phthalate diethylene glycol ester)

Polyol F was prepared in a similar manner to than of Polyol E, but with a 128 mg KOH/g PA-
10 DEG polyol as an initiator (438 g/eq); the initiator used is 2,965 grams of a 128 Ohv PA-DEG polyol,
along with 20.1 g of 45% KOH (aqueous) and 2,360 grams of propylene oxide to give a propoxylated
polyester ether polyol with an OH value of 82 mg KOH/g and subsequently finished/neutralized as
described in Example 2 above. Analysis of polyol E gave the following properties:

OH value = 83.5 mg KOH/g (ASTM E 222 method)

15 Dynamic viscosity = 22,050 cP @ 25°C (Brookfield, #31 spindle)

% Propylene oxide = 34.9% by weight

% Moisture = 0.11% (ASTM D 4672 method)

20 **Example 5: Preparation of Polyester-Ether Polyol G (propoxylated *ortho*-phthalate diethylene glycol ester)**

Polyol G is prepared in a manner similar to Polyol F (2,965 grams of a 128 Ohv PA-DEG
initiator, 20.1 grams of 45% KOH), but propoxylated (6,360 grams of propylene oxide) to an OH value
of 53.8 mg KOH/g and subsequently finished/neutralized. Analysis of polyol E gave the following
25 properties:

OH value = 53.8 mg KOH/g (ASTM E 222 method)

Dynamic viscosity = 4,710 cP @ 25°C (Brookfield, #31 spindle)

% Propylene oxide = 58% by weight

% Moisture = 0.02% (ASTM D 4672 method)

30

Prepolymer Preparation

Prepolymers are generally prepared by the reaction of a polyol with an isocyanate at about 60 - 70° C over a two hour period in a reactor equipped with agitation means and a slow nitrogen pad. The polyol is first warmed to 80°C followed by the addition of the required amount of isocyanate flakes to form a mixture. The mixture is then sealed and allowed to cool over a 12 hour period to about 25°C; the weight percent of unreacted isocyanate (% NCO) is then determined in accordance with test ASTM D 2582-80.

Dynamic viscosity is determined with a Brookfield RVT viscometer equipped with a # 31 spindle, Thermocel and temperature controller. Table III gives the prepolymer nomenclature, formulations and results.

Table III

Prepolymer Reference	Polyol Used and amount	Amount of MDI used	Final Prepolymer %NCO
H	Polyol A, 406.4 grams	393.6 grams	13.96
I	Polyol B, 389.6 grams	410.4 grams	14.85
J	Polyol D, 290 grams	309 grams	14.67
K	Polyol C, 200 grams	205 grams	14.75

Elastomer Preparation

Elastomers are prepared by hand mixing the appropriate amount of prepolymer (H – J) with 1,4-butane diol for approximately 15 seconds, followed by the addition of one drop of DBTDL catalyst and approximately 10 seconds of additional hand mixing and casting into metal molds which are preheated to about 120°C. Elastomer parts were cured by placing the mold in a 120°C oven for one hour, followed by removal and allowing the mold and contents to cool about 25°C for at least four hours before extracting parts. Table IV gives formulation data for the elastomer samples (L – N).

Table IV

Elastomer Designation	Prepolymer and amount	Amount of 1,4-butanediol
L	H, 310 grams	45 grams
M	I, 170 grams	22.7 grams
N	J, 294.9 grams	45 grams

Adhesion Sample Preparation

Adhesion samples were prepared by moistening 1" X 2" stainless steel strips (Q-Panel Lab Products) with a small amount of prepolymer (Table II) and then pressing a wood tongue depressor, by means of a five pound weight, onto the steel strip for 12 hours to form a bonded sample. The bonded samples were then evaluated using a "Pull apart test" approximately 24 hours later to classify

the method of failure, as detailed more fully as described below. The "Pull apart test" entails bonding two surfaces together with a particular material, allowing the bond to dry/cure at room temperature (i.e., 25°C) for approximately 24 hours, grasping both surfaces (one in each hand) and pulling the surfaces apart, followed by visual qualitative observation of the previously bonded surfaces to look for torn substrate fragments (substrate failure), torn adhesive (cohesive failure) or one clean surface (adhesive failure).

Elastomer Sample Evaluation

Elastomers prepared in Table IV were evaluated for Tensile Strength (ASTM D 638-91 method), Elongation (ASTM D 638-91 method) and Shore A and Shore D Hardness (ASTM D-2240-91 method). The results are presented below.

	<u>Elastomer L</u>	<u>Elastomer M</u>	<u>Elastomer N</u>
Tensile Str.(psi)	1614	1294	2163
Elongation (%)	269	96	84
Shore A/D Hardness	94/50	96/49	97/60

As can be seen by the above results, the formulation prepared from inventive Polyol D (in Elastomer L) exhibits greater tensile strength and elongation than that of Elastomer M, prepared from the conventional Polyol A, even though both specimens exhibit the same hardness.

Prepolymer Viscosity Evaluation (Brookfield RVT, #31 spindle, cP @ 25°C)

Prepolymer J 2250	Prepolymer H 1035	Prepolymer I 2340	Prepolymer K 25,500
----------------------	----------------------	----------------------	------------------------

As can be seen by the above results, the corresponding prepolymer of a pure PA-DEG polyester polyol is approximately 25,500 cP @ 25°C, where as the prepolymer of the polyester-ether polyol material is less than 10% of that viscosity, a highly desirable characteristic.

Adhesion Evaluations

For the metal-wood bond sample formed with prepolymer H, the failure method was cohesive; i.e., as an attempt was made to separate the wood and metal members by hand, both the wood and metal separated in tact, visibly undamaged and with adhesive residue on both the formerly bonded wood and metal surfaces.

For the metal-wood bond formed with Prepolymer J, the failure method was substrate; *i.e.*, as an attempt was made to separate the wood and metal by hand, the wood split, leaving fragments of wood bonded to the metal.

In accordance with these qualitative results, substrate failure is almost always preferred in structural (load-bearing members) bonding, since the adhesive is stronger than one of the substrates. Here, the PPG-prepolymer/adhesive failed undesirably, as compared to the prepolymer made from the novel polyester-ether polyol, *i.e.* the material gave a more desirable failure.

Solubility Evaluations

The following polyol materials shown in Table V were used to explore the solubility, *i.e.*, compatibility, of inventive polyester-ether polyols in other various ester- and ether-based polyols.

Table V

Designation	Polyol Name	OH value	Source	Description	Class
AA	Voranol 220-110	106.9	Dow	Polypropylene glycol	Polyether
BB	Voranol 220-056	55.28	Dow	Polypropylene glycol	Polyether
	Voranol 230-056	57.1	Dow	Glycerin- polypropylene oxide triol	Polyether
FF					
GG	Voranol 370	373	Dow	Sucrose-glycerin polypropylene oxide polyol	Polyether
HH	PolyG 85-36	36.94	Olin	Glycerin -polypropylene oxide triol, ethylene oxide capped	Polyether
II	StepanPol PS-2002	195	Stepan	Phthalic anhydride-diethylene glycol	Polyester
JJ	StepanPol PS-3152	315	Stepan	Phthalic anhydride-diethylene glycol	Polyester
KK	Terate 2541	237	Cape	Diethylene glycol terephthalate	Polyester
LL	Tone 0240	61.49	Union Carbide	Polycaprolactone	Polyester

Blends of Polyol E and each of polyols in Table V above are made at weight ratios of 25:50 grams, 50:50 grams and 75:50 grams, respectively, in six ounce, open-mouth, clear flint glass jars. Similar blends are made with Polyol G. In each case (at each weight ratio), all the mixtures were visibly clear (formed soluble systems).

When Polyol E (or polyol G) are replaced in an identical series of experiments with either Polyols I, J, or N no solubility at any level was observed with any of the polyether polyols (A, B, F, G, H).

Polyol D will dissolve in either polyether or polyester glycols which is necessary to make stable two-part systems. Essentially, PA-DEG propoxylated to 55 - 58% propylene oxide by weight will be soluble in either ether or ester glycols. More propylene oxide by weight makes the product soluble on PPGs only; less PO with an ester is soluble only in ester glycols.

Polyester-Ether Polyol Preparation Using Double Metal Cyanide Catalyst

Control/Comparative General Procedure Description

Polyester polyol initiator (such as PS-2002) is combined with KOH as catalyst (either 45% aqueous solution or powdered KOH may be utilized; if added as a solution, water is stripped to ≤ 0.10 wt. % after addition of the catalyst). This polyester polyol-catalyst solution is charged into a 2-gallon, stainless steel Chemineer alkoxylation reactor. Propylene oxide (PO) is added to reactor to maintain the following conditions: ≤ 125 °C temperature, ≤ 75 psi pressure, with initial N₂ pressure of 2-3 psi. After addition of PO, the reaction was "digested" - continued to react without further addition of PO - with agitation until the rate of pressure decrease observed for the reaction stabilized. The reactor is then vented, purged with N₂, and the contents were drained for further treatment.

The product of the propoxylation is vacuum stripped to remove any unreacted PO still present. Hydrogen peroxide is then added to improve the product's color. The product is then treated with Magnesol to remove the potassium catalyst, with stirring for at least one hour (to permit contact of Magnesol with water), vacuum stripped (to remove water added by Magnesol), and filtered (to remove the Magnesol/potassium amalgamated solids).

Example A (Using Standard KOH as Catalyst)

To approximately 3013g of PS-2002 polyol in a reactor equipped with agitation, N₂ sparging, heat, and vacuum was added approximately 49.8g of 45% aq. KOH solution (at KOH level of 0.2 wt-%-by-final-product-weight). The resulting solution was stripped to remove water under full vacuum at ≤ 130 °C for about 30 minutes (until water evolution stopped).

Next, approximately 2847g of the above solution was charged into alkoxylation reactor. Then, as outlined above, approximately 1745g of PO (6 mole PO/mole polyester diol) were added over 250 minutes, at an approximate rate of addition of about 330 g/hr of PO. Digestion with agitation was accomplished in about 2 hours and the time for subsequent neutralization and removal of the potassium was about 6 hours. The final product was treated with approximately 0.04 wt. % H₂O₂, based on the weight of the final product, to improve color, followed by treatment with Magnesol (2.0

%-by-wt.) to remove the potassium catalyst, stirred for at least one hour (to permit contact of Magnesol with water), vacuum stripped (to remove water), and filtered (to remove the Magnesol/potassium amalgamated solids).

Inventive Description and General Procedure (Using Double Metal Cyanide (DMC) Catalyst)

5 Polyester polyol initiator (such as PS-2002) is combined with the desired amount of DMC compound as catalyst. Generally, no stripping is necessary as no appreciable water is present. Then, the polyester polyol-catalyst solution is charged into a 2-gallon, stainless steel Chemineer alkoxylator reactor. Propylene oxide (PO) is then added to the reactor to maintain the following conditions: ≤ 125 °C temperature, ≤ 75 psi pressure, with initial N₂ pressure of 2-3 psi. After addition
10 of PO, the reaction is "digested" - continued to react without further addition of PO – with agitation until the rate of pressure decrease observed for the reaction stabilized. The reactor is then vented, purged with N₂, and the contents are drained for further treatment as desired. The product of the propoxylation is vacuum stripped to remove any unreacted PO still present.

A slight amount of hydrogen peroxide (e.g., 0.04 %-by-wt.) may optionally be added to
15 improve the product's color. The product may also be optionally treated with a sufficient amount of Magnesol (e.g., 2.0 %-by-wt.) to remove the catalyst, stirred for at least one hour (to permit contact of Magnesol with water), vacuum stripped (to remove water), and filtered (to remove the Magnesol/catalyst amalgamated solids).

Inventive Example B (Using Double Metal Cyanide Catalyst)

20 To approximately 3491g of PS-2002 was added 10.3g of DMC compound (at catalyst level of 0.2 wt.-%-by-final-product-weight); this solution was then charged into alkoxylator reactor. Then, as outlined above, approximately 2115g of PO (6 mole PO/mole polyester diol) were added over 90 minutes, at a rate of addition of about 2950 g/hr of PO. While the material was digested for two hours (to replicate conditions of above control), the pressure had stabilized after 30 minutes of digestion.

25 No additional time was required for subsequent handling of the material – no unreacted PO was found to be present. Approximately 0.04 wt. percent hydrogen peroxide was added to improve the product's color. The product was also treated with 2.0 wt. percent Magnesol, stirred for an one hour, vacuum stripped, and filtered (to remove the Magnesol/catalyst amalgamated solids).

Inventive Example C (Using Double Metal Cyanide Catalyst)

To approximately 3168g of a polyester polyol (99.5 OHV, 13.8 AV, PA/Glycerine/DEG polyester triol) was added 10.0g of DMC compound (at catalyst level of 0.18 wt-%-by-final-product-weight); this solution was charged into the alkoxylation reactor. Then, as outlined above, approximately 2460g of PO (22.6 mole PO/mole polyester diol) was added over 125 minutes, at a rate of addition of about 1225 g/hr of PO. The material was digested for two hours. The time for subsequent handling of the material was about 30 minutes – only stripping of unreacted PO was necessary. No hydrogen peroxide was needed to improve the product's color and no Magnesol was required to remove the catalyst.

All documents, e.g., patents and journal articles, cited above or below are hereby incorporated by reference in their entirety.

From the foregoing, it will be appreciated that although specific embodiments of the invention have been described herein for purposes of illustration, various modifications may be made without deviating from the spirit or scope of the invention.

WHAT IS CLAIMED:


1. A composition suitable for preparing urethane prepolymers and/or urethane foams or non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising:

(a) from about 0 % to about 5.0 % based on the weight of the composition of a urethane catalyst;

(b) from about 10% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:

(1) about 2 – 60 % based on the weight of the polyester-ether polyol of phthalic anhydride or phthalic acid; and

(2) about 40 - 98 % based on the weight of the polyester-ether polyol of at least one polyol of the formula:




wherein R₁ represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) -CH₂-R₂-CH₂-

where R₂ represents:



(c) -(R₃O)_{n2}-R₃-

where each R₃ independently is an alkylene group of about 2 to about 4 carbon atoms, and n2 is an integer of from about 1 - 200; and

(3) about 10 – 80 % based on the weight of the polyester-ether polyol of an alkoxyating agent;

(c) from about 0 - 50 percent by weight of an auxiliary polyether polyol, polyester polyol, or a mixture thereof;

(d) from about 0% to about 10% based on the weight of the composition of a blowing agent; and

(e) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant.


2. A composition according to claim 1, wherein the alkoxyating agent is ethylene oxide.

5

3. A composition according to claim 1, wherein the alkoxyating agent is propylene oxide.

4. A composition according to claim 3, wherein the urethane catalyst is tetramethylbutanediamine (TMEDA), 1,4-diaza(2,2,2)bicyclooctane (DABCO), dibutyltin dilaurate (DBTDL) tin octoate (SnOct), dimorpholine diethylether (DMDEE), or mixtures thereof.

5. A composition according to claim 4, wherein the polyester-ether polyol has the formula:




15

wherein R represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R_2 represents:



20


(c) $-(\text{R}_3\text{O})_{n2}-\text{R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and

$n2$ is an integer of from about 1 - 200; and

wherein R' and R'' are independently $-\text{[CH}_2\text{CH}_2\text{O]}_{n1}-$, $-\text{[CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n1}-$, $-\text{[CH}_2\text{CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n1}-$,
or a random combination thereof, where n1 is independently 1-200 independently for R' and R''; and
wherein n is 1 - 200.


6. A composition according to claim 5, wherein the polyester-ether polyol has the
formula:



wherein R represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R₂ represents:



- (c) $-(\text{R}_3\text{O})_{n2}-\text{R}_3-$


where each R₃ independently is an alkylene group of about 2 to about 4 carbon atoms, and

n2 is an integer of from about 1 - 200; and

where n1 is independently 1-200; and

wherein n is 1 - 200.

7. A composition according to claim 6, wherein the polyester-ether polyol has the
formula:



wherein each R is $-(CH_2CH_2OCH_2CH_2)-$; wherein each n_1 is independently 1-200; and

wherein $n = 1 - 200$.

5

8. A composition according to claim 1, comprising from about 3 – 40 %, based on the weight of the composition, of the auxiliary polyether-based or polyester-based polyol, or a mixture thereof.

10

9. A composition according to claim 1, comprising from about 5 - 35 %, based on the weight of the composition, of the auxiliary polyether-based or polyester-based polyol, or a mixture thereof.

15

10. A urethane prepolymer, urethane foam or non-foam urethane suitable for use in a coatings, adhesives, sealants and/or elastomers, the prepolymer, foam or non-foam urethane made by polymerizing the composition of claim 1.

20

11. A composition suitable for preparing urethane prepolymers and/or urethane foams or non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising:


(a) from about 10 % to about 60% based on the weight of the composition of an isocyanate;

(b) from about 50% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:

25

(1) about 2 - 60 % based on the weight of the polyester-ether polyol of phthalic anhydride or phthalic acid; and


(2) about 40 - 98 % based on the weight of the polyester-ether polyol of at least one polyol of the formula:



wherein R_1 represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
 (b) $-\text{CH}_2\text{-R}_2\text{-CH}_2-$

where R_2 represents:



- (c) $-(\text{R}_3\text{O})_{n2}\text{-R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and $n2$ is an integer of from about 1 - 200; and

(3) about 10 – 80 % based on the weight of the polyester-ether polyol of an alkoxyating agent.


- (c) from about 0 - 50 % based on the weight of the composition of an auxiliary polyether polyol, polyester polyol, or a mixture thereof;
 (d) from about 0% to about 10% based on the weight of the composition of a blowing agent; and
 (e) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant.

12. A composition according to claim 11, wherein the alkoxyating agent is ethylene oxide.

13. A composition according to claim 11, wherein the alkoxyating agent is propylene oxide.

14. A composition according to claim 13, wherein the isocyanate is 2,4- and/or 2,4/2,6-toluene diisocyanate, diphenyl methane 4,4'-diisocyanate, hexamethylene diisocyanate, isophorone diisocyanate, or mixtures thereof.


15. A composition according to claim 14, wherein the polyester-ether polyol has the formula:



wherein R represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R_2 represents:




- (c) $-(\text{R}_3\text{O})_{n2}-\text{R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and

$n2$ is an integer of from about 1 - 200; and

wherein R' and R'' are independently $-\text{[CH}_2\text{CH}_2\text{O]}_{n1}-$, $-\text{[CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n1}-$, $-\text{[CH}_2\text{CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n1}-$, or a random combination thereof, where $n1$ is independently 1-200 independently for R' and R'' ; and wherein n is 1 - 200.


16. A composition according to claim 15, wherein the polyester-ether polyol has the formula:



wherein R represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R_2 represents:



- (c) $-(\text{R}_3\text{O})_{n2}-\text{R}_3-$


where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and

$n2$ is an integer of from about 1 - 200; and

where $n1$ is independently 1-200; and

wherein n is 1 - 200.

17. A composition according to claim 16, wherein the polyester-ether polyol has the formula:



wherein each R is $-(\text{CH}_2\text{CH}_2\text{OCH}_2\text{CH}_2)-$; wherein each $n1$ is independently 1-200; and

wherein $n = 1 - 200$.

18. A composition according to claim 11, comprising from about 3 – 40 %, based on the weight of the composition, of the auxiliary polyether-based or polyester-based polyol, or a mixture thereof.

5 19. A composition according to claim 18, comprising from about 5 - 35 % based on the weight of the composition, of the auxiliary polyether-based or polyester-based polyol, or a mixture thereof.

10 20. A urethane prepolymer, urethane foam or non-foam urethane suitable for use in a coating, adhesive, sealant and/or elastomer, the prepolymer, foam or non-foam urethane made by polymerizing the composition of claim 11.

21. A composition suitable for preparing urethane prepolymers and/or urethane foams or non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising:


15 (a) from about 10 % to about 70% based on the weight of the composition of an isocyanate;

(b) from about 0.02 % to about 5.0 % based on the weight of the composition of a urethane catalyst; and

(c) from about 50% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:

(1) about 2 - 60 % based on the weight of the polyester-ether polyol of phthalic anhydride or phthalic acid; and

(2) about 40 - 98 % based on the weight of the polyester-ether polyol of at least one polyol of the formula:





wherein R₁ represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) $-\text{CH}_2\text{-R}_2\text{-CH}_2-$

where R₂ represents:



where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and $n2$ is an integer of from about 1 - 200; and

(3) about 10 – 80 % based on the weight of the polyester-ether polyol of an alkoxyating agent selected from the group consisting essentially of ethylene oxide, propylene oxide or butylene oxide or mixtures thereof;

(d) from about 0 - 50 % based on the weight of the composition of an auxiliary polyether polyol, polyester polyol, or a mixture thereof;

(e) from about 0% to about 10% based on the weight of the composition of a blowing agent; and

(f) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant.


22. A composition according to claim 21, wherein the alkoxyating agent is ethylene oxide.

23. A composition according to claim 21, wherein the alkoxyating agent is propylene oxide.

24. A composition according to claim 21, wherein the isocyanate is 2,4- and/or 2,4/2,6-toluene diisocyanate, diphenyl methane 4,4'-diisocyanate, hexamethylene diisocyanate, isophorone diisocyanate, or mixtures thereof.

25. A composition according to claim 24, wherein the urethane catalyst is tetramethylbutanediamine (TMEDA), 1,4-diaza(2,2,2)bicyclooctane (DABCO), dibutyltin dilaurate (DBTDL) tin octoate (SnOct), dimorpholine diethylether (DMDEE), or mixtures thereof.


26. A composition according to claim 25, wherein the polyester-ether polyol has the formula:



5 wherein R represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R_2 represents:




- (c) $-(\text{R}_3\text{O})_{n2}-\text{R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and $n2$ is an integer of from about 1 - 200; and

wherein R' and R'' are independently $-\text{[CH}_2\text{CH}_2\text{O]}_{n1}-$, $-\text{[CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n1}-$, $-\text{[CH}_2\text{CH}_2\text{CH}(\text{CH}_3)\text{O]}_{n1}-$, or a random combination thereof, where $n1$ is independently 1-200 independently for R' and R'' ; and
 wherein n is 1 - 200.

27. A composition according to claim 26, wherein the polyester-ether polyol has the formula:




wherein R represents:

(a) alkylene groups of about 2 to 10 carbon atoms;

(b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R_2 represents:



(c) $-(\text{R}_3\text{O})_{n_2}-\text{R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and


n_2 is an integer of from about 1 - 200; and

where n_1 is independently 1-200; and

wherein n is 1 - 200.

28. A composition according to claim 27, wherein the polyester-ether polyol has the

formula:



wherein each R is $-(\text{CH}_2\text{CH}_2\text{OCH}_2\text{CH}_2)-$; wherein each n_1 is independently 1-200; and

wherein $n = 1 - 200$.


29. A composition according to claim 21, comprising from about 3 - 40 %, based on the

weight of the polyester-ether polyol, of the auxiliary polyether-based or polyester-based polyol, or a mixture thereof.

30. A composition according to claim 29, comprising from about 5 - 35 %, based on the weight of the polyester-ether polyol, of the auxiliary polyether-based or polyester-based polyol, or a mixture thereof.

31. A urethane prepolymer, urethane foam or non-foam urethane suitable for use in a coating, adhesive, sealant and/or elastomer, the prepolymer, foam or non-foam urethane made by polymerizing the composition of claim 21.


32. A polyester-ether polyol for use in preparing urethane prepolymers, urethane foams and non-urethane coatings, sealants, adhesives and/or elastomers of the formula:



wherein R represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2-\text{R}_2-\text{CH}_2-$

where R_2 represents:




- (c) $-(\text{R}_3\text{O})_{n2}-\text{R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and $n2$ is an integer of from about 1 - 200; and

where $n1$ is independently 1-200; and

wherein n is 1 - 200.

33. A polyester-ether polyol for use in preparing urethane prepolymers, urethane foams and non-urethane coatings, sealants, adhesives and/or elastomers of the formula:




wherein each R is $-(CH_2CH_2OCH_2CH_2)-$; wherein each n_1 is independently 1-200; and

wherein $n = 1 - 200$.

5

34. A method for preparing a phthalate polyester-ether polyol comprising the steps of combining


- a) about 2 - 60 % based on the weight of phthalate polyester-ether polyol of phthalic anhydride or phthalic acid; and
- b) about 40 - 98 % based on the weight of phthalate polyester-ether polyol of at least one polyol of the formula:



wherein R_1 represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-CH_2-R_2-CH_2-$

where R_2 represents:



- (c) $-(R_3O)_{n_2}-R_3-$

20

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and n_2 is an integer of from about 1 - 200,

to form an intermediate polyester-polyol; and alkoxyating said intermediate polyester polyol with about 10 - 80 % based on the weight of the phthalate polyester-ether polyol of an alkoxyating agent to form the polyester-ether polyol.


35. A method according to claim 34, wherein the alkoxylation is conducted in the presence of a double metal cyanide complex catalyst.

36. A method according to claim 35, wherein the double metal cyanide complex catalyst is of the formula




wherein M^1 represents at least one of Zn(II), Fe(II), Co(II), Ni(II), Mn(II), Cu(II), Sn(II) or Pb(II); M^2 represents at least one of Fe(II), Fe(III), Co(III), Cr(III), Mn(II), Mn(III), Ir(III), Rh(III), Ru(II), V(IV) or V(V); M^3 represents M^1 and/or M^2 ; A, D and E each represent an anion which may be the same or different; L represents an alcohol, aldehyde, acetone, ether, ester, amide, nitrile or sulphide or mixtures thereof; a and d are numbers to satisfy the valency state of M^1 and M^2 in the double metal cyanide part of the general formula I; b and c are integers ($b > c$) which together with a and d provide the electroneutrality of the double metal cyanide part of the general formula I; e is an integer satisfying the valency state of M^3 ; n and m are integers satisfying the electroneutrality of HE, and w is a number between 0.1 and 4; x is a number up to 20; y is a number between 0.1 and 6, and z is a number between 0.1 and 5.

37. A method according to claim 35, wherein the double metal cyanide complex catalyst is of the formula



wherein X represents a halide; M^3 represents Zn(II), Co(II) or Fe(II); L represents an alcohol, ether or ester and w is a number between 0.7 and 1.5; x is a number between 2 and 10; y is a number between 1.5 and 3, and z is a number between 0.15 and 1.5.

38. A method according to claim 35, wherein the double metal cyanide complex catalyst is of the formula




39. A polyester-ether polyol produced by the method of claims 35, 36 or 37.

40. A method for preparing urethane prepolymers, urethane foams and non-foam urethane coatings, adhesives, sealants and/or elastomers, comprising combining:

- (a) from about 10 % to about 60% based on the weight of the composition of an isocyanate;
- (b) from about 0.02 % to about 5.0 % based on the weight of the composition of a urethane catalyst; and
- (c) from about 50% to about 90% based on the weight of the composition of a phthalate polyester-ether polyol which is the reaction product of:


- (1) about 2 - 60 % based on the weight of phthalate polyester-ether polyol of phthalic anhydride or phthalic acid; and
- (2) about 40 - 98 % based on the weight of phthalate polyester-ether polyol of at least one polyol of the formula:



wherein R_1 represents:

- (a) alkylene groups of about 2 to 10 carbon atoms;
- (b) $-\text{CH}_2\text{-R}_2\text{-CH}_2-$

where R_2 represents:



- (c) $-(\text{R}_3\text{O})_{n2}\text{-R}_3-$

where each R_3 independently is an alkylene group of about 2 to about 4 carbon atoms, and $n2$ is an integer of from about 1 - 200; and

- (3) about 10 - 80 % based on the weight of phthalate polyester-ether polyol of an alkoxylating agent; and

- (d) from about 0 - 50 % based on the weight of the composition of an auxiliary polyether polyol, polyester polyol, or a mixture thereof;

(e) from about 0% to about 10% based on the weight of the composition of a blowing agent;

(f) from about 0% to about 5% based on the weight of the composition of a compatibilizing surfactant,

5 to form a mixture; and

reacting/polymerizing the mixture to form a urethane prepolymer, urethane foam or non-foam urethane coating, adhesive, sealant and/or elastomer.

ABSTRACT OF THE DISCLOSURE

Disclosed are polyester-ether polyols and their use in urethane prepolymers, urethane foams and non-foam urethane coatings, adhesives, sealants and/or elastomers. Methods for producing such polyester-ether polyols using double metal cyanide catalysts are disclosed, along with methods for producing urethane prepolymers. The polyester-ether polyols of the instant invention are preferably the reaction product of phthalic anhydride, diethylene glycol, and propylene oxide. These polyester-ether polyols are useful as either the primary polyol in urethane compositions or in combination with conventional auxiliary polyester- and/or polyether-based polyols. The polyester-ether polyols impart greatly improved solubility and compatibility to mixtures of either polyether and/or polyester polyols. The polyester-ether polyols of the instant invention are desirably of lower viscosity than their precursor intermediate polyester polyols and are generally soluble in either polyester- and/or polyether-based polyols. Additionally, the polyester-ether polyols generally provide improved hydrolytic stability to CASE materials in which they are utilized.

POWER OF ATTORNEY

As named inventors, we hereby appoint the following registered practitioner(s)

Paul S. Tully

Registration Number 44,377

to prosecute this application for letters Patent of the United States, entitled:

**PHTHALIC ANHYDRIDE BASED POLYESTER-ETHER POLYOLS AND DOUBLE METAL
CYANIDE CATALYST SYSTEM FOR PREPARING SAME**

and identified as

Case No. T99,005-B

and transact all business in the Patent and Trademark Office connected therewith.

SEND CORRESPONDENCE TO

DIRECT TELEPHONE CALLS TO:

Paul S. Tully
Stepan Company
22 W. Frontage Road
Northfield, IL 60093

Paul S. Tully
(847) 501-2219

Full name of first inventor (given name, family name):

Inventors Signature:


Douglas K. Hillshafer

Date:

October 25, 2000

Residence:

4224 Clausen
Western Springs, Illinois 60058

Citizenship:

U.S.

Post Office Address:

4224 Clausen

~~Cook~~ ~~Kane~~ County

Western Springs, Illinois 60058

Full name of second inventor (given name, family name):

Inventors Signature: Eric J. Geiger
Eric J. Geiger

Date: 10/25/00

Residence: 31 S. Elm Avenue
Fox Lake, Illinois 60020

Citizenship: U.S.

Post Office Address: 31 S. Elm Avenue
Lake County
Fox Lake, Illinois 60020

Please type a plus sign (+) inside this box ☐

PTO/SB/01 (12-97)
Approved for use through 9/30/00. OMB 0651-0032
Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63) <input checked="" type="checkbox"/> Declaration Submitted with Initial Filing OR <input type="checkbox"/> Declaration Submitted after Initial Filing (surcharge (37 CFR 1.16 (e)) required)	Attorney Docket Number	T99,005-B
	First Named Inventor	Geiger, Eric J.
	COMPLETE IF KNOWN	
	Application Number	
	Filing Date	October 25, 2000
	Group Art Unit	
	Examiner Name	

As a below named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**PHTHALIC ANHYDRIDE BASED POLYESTER-ETHER POLYOLS AND
DOUBLE METAL CYANIDE CATALYST SYSTEM FOR PREPARING SAME**

the specification of which ☒ is attached hereto OR ☐ was filed on (MM/DD/YYYY) [] as United States Application Number or PCT International Application Number [] and was amended on (MM/DD/YYYY) [] (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or 356(b) of any foreign application(s) for patent or inventor's certificate, or 356(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
			<input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/>	<input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/>	<input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto

I hereby claim the benefit under 35 U.S.C. 119(e) of any United States provisional application(s) listed below

Application Number(s)	Filing Date (MM/DD/YYYY)

☐ Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

[Page 1 of 2]

Burden Hour Statement. This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO Assistant Commissioner for Patents, Washington, DC 20231

Please type a plus sign (+) inside this box → ☐

PTO/SB/01 (12-97)
Approved for use through 9/30/00 OMB 0651-0032
Patent and Trademark Office, U. S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number

DECLARATION — Utility or Design Patent Application

I hereby claim the benefit under 35 U.S.C. 120 of any United States application(s), or 365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application or PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)
09/427,050	10/25/99	

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority data sheet PTO/SB/02C attached hereto.

As a named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

☐ Customer Number

OR

☒ Registered practitioner(s) name/registration number listed below

Place Customer
Number Bar Code
Label here

Name	Registration Number	Name	Registration Number
Paul S. Tully	44,377		

☐ Additional registered practitioner(s) named on supplemental Registered Practitioner Information sheet PTO/SB/02C attached hereto.

Direct all correspondence to. ☐ Customer Number or Bar Code Label ☒ Correspondence address below

Name	Paul S. Tully, Stepan Company				
Address	Intellectual Property Department				
Address	22 W. Frontage Road				
City	Northfield	State	IL	ZIP	60015
Country	USA	Telephone	847-501-2219	Fax	847-446-9359

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true, and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor: ☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))	Family Name or Surname
Eric J.	Geiger

Inventor's Signature	<i>Eric J. Geiger</i>			Date	10/25/00
Residence City	Fox Lake	State	Illinois	Country	USA
				Citizenship	US
Post Office Address	31 S. Elm Avenue				
Post Office Address					
City	Fox Lake	State	IL	ZIP	60020
				Country	USA

☒ Additional inventors are being named on the 1 supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto

Please type a plus sign (+) inside this box → +

PTO/SB/02A (3-97)

Approved for use through 9/30/98 OMB 0651-0032
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number

DECLARATION

ADDITIONAL INVENTOR(S) Supplemental Sheet

Page 1 of 1

Name of Additional Joint Inventor, if any:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle [if any])

Family Name or Surname

Douglas K.

Hillshaffer

Inventor's
Signature

Douglas K. Hillshaffer

10/21/00
Date

Residence: City

Western Springs

State

IL

Country

USA

Citizenship

US

Post Office Address

4224 Clausen

Post Office Address

City

Western Springs

State

IL

ZIP

60058

Country

USA

Name of Additional Joint Inventor, if any:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle [if any])

Family Name or Surname

Inventor's
Signature

Date

Residence: City

State

Country

Citizenship

Post Office Address

Post Office Address

City

State

ZIP

Country

Name of Additional Joint Inventor, if any:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle [if any])

Family Name or Surname

Inventor's
Signature

Date

Residence: City

State

Country

Citizenship

Post Office Address

Post Office Address

City

State

ZIP

Country

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO Assistant Commissioner for Patents, Washington, DC 20231.